

PRV

PATENT- OCH REGISTRERINGSVERKET  
Patentavdelningen

Rec'd PCT/PTO 07 DEC 2004

PCT/SE 03 / 0 1 0 17

10/517226

**Intyg  
Certificate**

*Härmed intygas att bifogade kopior överensstämmer med de handlingar som ursprungligen ingivits till Patent- och registreringsverket i nedannämnda ansökan.*

*This is to certify that the annexed is a true copy of the documents as originally filed with the Patent- and Registration Office in connection with the following patent application.*



(71) Sökande                      Amersham Biosciences AB, Uppsala SE  
Applicant (s)

(21) Patentansökningsnummer    0202016-2  
Patent application number

(86) Ingivningsdatum                      2002-06-27  
Date of filing

REC'D 03 JUL 2003

WIPO                      PCT

Stockholm, 2003-06-25

*För Patent- och registreringsverket  
For the Patent- and Registration Office*

*Sonia André*  
Sonia André

Avgift  
Fee

**PRIORITY DOCUMENT**  
SUBMITTED OR TRANSMITTED IN  
COMPLIANCE WITH  
RULE 17.1(a) OR (b)

**BEST AVAILABLE COPY**

**PATENT- OCH  
REGISTRERINGSVERKET  
SWEDEN**

Postadress/Address  
Box 5055  
S-102 42 STOCKHOLM

Telefon/Phone  
+46 8 782 25 00  
Vx 08-782 25 00

Telex  
17978  
PATOREG S

Telefax  
+46 8 666 02 86  
08-666 02 86

## POLYMERIC SUPPORT HAVING NOVEL PORE STRUCTURES

### Technical field

The present invention relates to the preparation of cross-linked polymeric supports that are useful e.g. in separation methods, and more specifically to a method of producing a cross-linked polymeric support useful as a chromatographic matrix, which support exhibits a novel pore structure. The invention also encompasses porous cross-linked polymeric supports as such as well as a method of modifying such supports with functional groups useful as ligands in chromatography.

### Background

Cross-linked, porous polymeric supports, such as particles, are useful as adsorbents in methods for separation and purification of organic and inorganic materials, such as in chromatographic separation and filtration methods. Further applications of such supports are e.g. as microcarriers for cell culture and as supports for solid-phase peptide or DNA synthesis. The supports should be chemically compatible to organic solvents over a wide range of pH and should have a desired shape, size, and porosity and surface area.

The porosity, and the nature of the pores, are properties that have been shown to be of specific importance in chromatographic methods for purification of target molecules, since an increased porosity will result in an increased surface area and accordingly a potentially increased binding capacity.

Furthermore, a general problem in chromatography, adsorption processes, heterogeneous catalysis etc where porous particles are used, is that the mass transport rate is strongly dependent on the particle size. Rapid mass transport can be achieved by decreasing the particle size, but small particles will also increase the backpressure of the packed beds. Hence, a trade-off must be made between

the mass transport rate and the pressure-flow properties. One way to improve the mass transport in a porous particle is to increase the total pore surface. Hierarchical pore structures have for example been suggested, wherein large feeder pores from the particle surface open into a network of smaller pores with a large surface available for adsorption.

One way of providing such a pore system has been disclosed by EP 0 222 718 (Mosbach and Nilsson), which suggests to solve the above-discussed mass transport problem by introducing cavities in their particles. More specifically, EP 0 222 718 discloses a method, wherein a solid cavity-generating compound is added to an aqueous solution comprising a matrix material, emulsifier is added, particles are formed by dispersion and finally said cavity-generating compound is leached out to leave behind cavities in the particles. An illustrative cavity-generating compound is calcium carbonate, and an illustrative added amount thereof is up to 10% by weight, corresponding to 3.6 % by volume. However, at such low amounts of cavity-forming compound, the pores will not make contact with each other, resulting in a closed-cell porous structure.

A specific technology for creating very small cavities in a polymer particle using a removable target compound is known as molecular imprinting. As the name implies, molecules are used as targets and are more specifically coupled to a polymeric chain via hydrogen bonding. The molecules used are for example drug targets, such as alkaloids, and the cavity left can be described as an imprint of the used target molecule and is accordingly limited to isolation of that same molecule kind. Moreover, molecular imprinting is limited to applications wherein microdimensional pore systems are desired.

USP 5,895,263 (Carter et al) discloses how materials degradable by heating can be used in a process for forming an integrated circuit device. Porous organic polysilica, which is a dielectric material, is first dissolved in a solution of a

decomposable polymer. The mixture obtained is heated in order to condense the organic polysilica. Finally, the decomposable polymer is decomposed uniformly, e.g. by exposure to radiation, within the matrix of the condensed rigid organic polysilica. The product obtained has improved mechanical toughness, crack resistance and dielectric properties. Consequently, the product can also be used as a protective coating for optical articles, such as glasses, contact lenses and solar reflectors.

WO 01/09204 (Symyx Technologies) discloses a method of producing controlled-architecture polymers. More specifically, the disclosed architected polymers are comprised of polyacrylamide repeating units having properties that are advantageous in electrophoretic separation systems, since the sieving capability of the partially branched or cross-linked polymer will be enhanced as compared to linear non-cross-linked polymers having the same repeating unit. However, sieving is not an essential property for polymer supports intended for use as chromatographic matrices, since other properties such as the above-discussed available surface area and mass transport are then of much greater importance. The method utilises living-type or semi-living type free radical polymerisation.

At the moment, free radical suspension polymerisation is the most widely used technique in the preparation of synthetic polymer supports for heterogeneous catalysts, ion exchange resins, chromatography media, peptide synthesis etc. Pore structures are then mainly provided by incorporation of a porogen and/or control of the level of cross-linking in the resin.

Atom transfer radical polymerisation (ATRP), which is a metal/ligand catalysed polymerisation, has offered a relatively new perspective on the synthesis of polymeric resins. One of the advantages with ATRP is that it provides a high degree of control over the polymerisation process. USP 5,763,548 (Maty-

jaszewsk et al) describes in detail conditions and components used in an ATRP process for preparing plastics, elastomers, adhesives, emulsifiers, or thermo-plastic elastomers.

#### Summary of the present invention

One object of the present invention is to provide a method of producing cross-linked polymeric supports of multimodal pore structures. This can be achieved by a method as defined in claim 1 and the claims dependent thereon.

Another object of the invention is to provide a method of producing porous cross-linked polymeric supports, which enables the definition of the morphology of the supports produced. This can be achieved by use of a method as described above, wherein the amount and/or nature of initiator molecule is carefully controlled. Alternatively or additionally, this can be achieved by controlling the composition of the monomer feed to the polymerisation process.

A further object of the present invention is to provide porous cross-linked polymeric supports with pendant functionalities.

Yet another object of the invention is to provide porous cross-linked polymeric supports that have different functionalities on the support surface, in the primary pore system and on the surface within the larger secondary pore system.

Further embodiments and advantages of the present invention will appear from the detailed description and the experimental part below.

#### Brief description of drawings

Figure 1 illustrates how an organic droplet phase is polymerised by suspension polymerisation and subsequently transformed into a polymer particle comprising a secondary pore structure in accordance with the present invention.

Figure 2 shows schematically how the secondary pore structure produced according to the present invention can be surface modified.

Figure 3 shows schematically how the primary pore structure produced according to the present invention can be surface modified.

Figure 4 shows FTIR spectra of (a) beads A4; (b) beads B4; (c) beads E4; (d) beads F4; (e) beads G4; (f) beads H4.

Figure 5 shows FTIR spectra of (a) beads A4; (b) beads C4; (c) degradation product of C4; (d) beads B4; (e) beads.

Figure 6 is a SEM photograph of a cross-section of beads A1.

Figure 7 is a SEM photograph of a cross-section of beads B1.

Figure 8 is a photograph of beads A1 obtained by optical light microscopy.

Figure 9 is a photograph of beads B1 obtained by optical light.

Figure 10 shows Table 1, naming polydivinylbenzene beads initiated by Boltorn®-BiB macroinitiators and mediated by CuCl/PMDETA.

Figure 11 shows Table 2, illustrating the hydrolytic degradation of the polyester portion of poly(Boltorn®-BiB-divinylbenzene) beads.

### Definitions

The term "initiator molecule" means herein an organic compound that comprises at least one site from which a radical polymerisation can be initiated. The term includes initiator molecules of different sizes, such as lower molecular compounds, including dimers, trimers and oligomers, and macromolecules. The term "multi-initiator" is used herein for an initiator molecule that comprises two or more initiator sites.

The term "macroinitiator" means herein an initiator molecule, which is a macromolecule and which comprises at least one initiating site.

The term "macromolecule" means herein a molecule that comprises a large number of monomeric units and has a number average molecular weight ( $M_n$ ) of at least about 500.

The term "degradable" means in the present context that it is possible to remove by chemical or physical degradation thereof.

The term "multimodal" pore structure means a structure that can be created in two or more modes, such as pore systems of differing sizes and/or pore systems created at different times.

The term "support" as used herein means a matrix suitable for use as a carrier of functional groups in an isolation process, such as a chromatographic procedure. The term "support" includes particles, monoliths and membranes.

The term "dendritic" compound is used in its conventional meaning to denote an isotropically soluble polymer that exhibits a tree-like structure.

The term "porogen" refers to an inert solvent (low molecular weight or polymeric), or a mixture of inert solvents, which is present during a polymerisation reaction wherein it gives rise to formation of a porous polymer at some stage during the polymerisation.

#### Detailed description of the invention

A first object of the present invention is a method of producing a cross-linked polymeric support having a multimodal pore structure, which method comprises the steps of

- (a) providing a degradable initiator molecule;
- (b) providing an organic phase, which comprises said initiator molecule, one or more radically polymerisable monomers and a porogen in a solvent, and an aqueous phase, which comprises a transition metal catalyst;
- (c) forming a suspension of the organic phase and the aqueous phase;
- (d) starting a suspension polymerisation of the organic phase in the aqueous phase by adding a ligand, which co-ordinates to the transition metal in the aqueous phase via at least one atom, to produce a cross-linked polymeric support having a primary pore structure and comprising initiator molecule; and

- (e) subjecting the support obtained from step (d) to degrading conditions to at least partially remove the initiator molecule from within the support to produce a cross-linked polymeric support having a secondary pore structure in addition to the primary pore structure.

Thus, the present method uses the principles of atom transfer radical polymerisation (ATRP) in an otherwise conventional suspension polymerisation process. For a general description of ATRP, see e.g. Wang et al. (in J. Am. Chem. Soc., 1995, 36, 2973; and in Macromolecules, 1995, 28, 7572). In brief, in ATRP, the initiation system is based on the reversible formation of growing radicals in a redox reaction between various transition metal compounds and an initiator. The present invention suggests for the first time to use atom transfer radical polymerisation in the production of polymeric supports that are porous. The multimodal pore structure including primary and secondary pores obtained according to the present method renders the supports especially useful as matrices in chromatographic methods.

In one embodiment of the present method, the initiator molecule provided in step (a) is obtained from commercial sources. For example, low molecular initiator molecules, such as 1-phenylethyl chloride or ethyl 2-bromoisobutyrate, are available e.g. from Acros or Aldrich. The initiator molecules can be inorganic or organic molecules, but are preferably organic compounds. In the present method, step (a) is understood to provide either one kind of initiator molecule or a mixture of two or more different initiator molecules.

In an alternative embodiment, step (a) comprises reacting a compound that has at least one hydroxy group, primary amine group or secondary amine group with an alfa-haloacyl halide. Thus, the reaction is either an esterification or an amidation performed according to conventional methods. An illustrative example of a suitable alfa-haloacyl halide is 2-bromoisobutyryl bromide (BiB),

which is commercially available e.g. from Aldrich. More examples of alfa-haloacyl halides are e.g. 2-bromopropionyl bromide, 2-bromo-iso-valeryl bromide and 2-bromo-iso-butyryl chloride.

In one embodiment, the initiator molecule provided in step (a) is a macroinitiator. Macroinitiators useful in the present invention can have virtually any three-dimensional structures, such as a dendritic structure, including star-shaped and hyperbranched structures.

In an advantageous embodiment, the initiator molecule is synthesised by reacting a hydroxy-functional dendritic polyester with an alfa-haloacyl halide, resulting in a polyester macroinitiator. Hydroxy-functional polyesters are commercially available, e.g. Boltorn® from Perstorp Chemicals AB (Sweden), which is available in five generations and thus offers a convenient variety in size of the secondary pores created by their removal with little change in chemistry.

Dendritic polyesters useful as starting materials in the synthesis of a macroinitiator can also be prepared as described in WO 93/17060 (Hult et al) or WO 99/00440 (Ihre et al).

In an alternative embodiment, the initiator molecule is synthesised by reacting an amino-functional dendritic polyamide with an alfa-haloacyl halide, resulting in a polyamide macroinitiator. Amino-functional polyamides can for example be prepared as described in Tomalia et al (Angew. Chem. Int. Ed. Engl. 29, p. 138-175), describing the preparation of dendritic polyamide amines.

In one embodiment, the initiator molecule used in the present method can be prepared in the desired size by reacting a specified generation of a dendritic initiator molecule with an alfa-haloacyl halide. As mentioned above, some

commercially available starting materials such as Boltorn® are available in several generations. Similarly, the synthesis of polyesters and/or amides can be performed in order to provide the desired generation of the dendritic molecule. Thus, one advantage with the present method is that by carefully selecting the size of the initiator molecule, the secondary pore size in the final product can be controlled. Thus, the novel kind of pores that is provided by removal of the initiator molecule can be defined by the size of the initiator molecule used. In addition, the novel pores can also consist of interlinks between the more conventional primary pores that originate from the porogen and/or monomer composition. Both the cavities formed where the initiator molecule is removed and the above-mentioned interlinks are part of the secondary pore structure, which is a kind of pore structure that cannot be achieved under conventional suspension polymerisation conditions.

Furthermore, even though the above-discussed USP 5,763,548 describes the principles of atom transfer radical polymerisation (ATRP), the conditions defined therein do not correspond to a conventional suspension polymerisation, such as the suspension polymerisation utilised according to the present invention. Furthermore, USP 5,763,548 describes ATRP for the preparation of solid articles, such as plastics, elastomers and the like, and nothing therein suggests that ATRP would be especially advantageous for the purpose of preparing porous polymeric supports. Accordingly, the present invention utilises for the first time the principles of ATRP with suspension polymerisation. In addition, the present invention combines such a polymerisation with the use of a degradable initiator molecule in order to provide a bimodal pore structure in the product.

The organic phase can be prepared in any suitable solvent, or mixture of solvents, conventionally used for suspension polymerisation, such as toluene, hexanone etc.

In one embodiment, the organic phase comprises up to 50%, such as about 30%, e.g. 32%, of initiator molecule, calculated as weight initiator molecule/weight main monomer. However, as the skilled person in this field will realise, the upper limit of the initiator molecule that can be provided in the organic phase will depend on the nature of the further components. For example, if a monomer feed that results in a more rigid polymer structure is used, then the proportion of initiator can be higher, the upper limit being determined by the risk of collapse of the final product. Accordingly, the intended use of the polymeric support produced will also be a factor to consider when the proportions of the components of the organic phase are decided.

The monomers present in the organic phase should provide for both polymerisation and cross-linking and the only requirement thereof is that they should be radically polymerisable. As is easily realised, in order to obtain a cross-linked product, at least one monomer present in the organic phase needs to be multifunctional. Thus, in one embodiment, the monomers are synthetic mono and/or multifunctional monomers, such as styrene and/or divinyl benzene.

In an advantageous embodiment, the organic phase also comprises one or more functional monomers, i.e. monomers that firstly comprise one vinyl group, which will be able to participate in the polymerisation, and secondly another functional group, which is not a vinyl group. Such a non-vinyl functional group can e.g. be a hydroxyl, an amine, or any other group that can subsequently be used for other purposes than forming the polymeric structure of the support.

The skilled person who uses the method according to the invention can easily decide what kind of further functionalities that are needed for each intended purpose. One illustrative such further functionality is an easily accessible chemical handle for further derivatisation of supports intended for use as chromatographic matrices.

In the present context, the term "bulk monomers" is used for the monomers that are added in large amounts to contribute to the basic polymeric structure of the support.

Mixtures of different monomers can also be provided in the organic phase.

Examples of useful monomers are also illustrated in the above-discussed USP 5,763,548.

Finally, in order to obtain the primary pore structure, the organic phase also comprises a conventional porogen. In a convenient embodiment, the solvent also acts as a porogen. Suitable porogens for use in this context are well known in this field, and the skilled person can easily make a selection among the commercially available products. As the skilled person in this field will realise, the primary pore structure will also be affected by components of the monomer feed.

Any transition metal compound that can participate in a redox cycle with the initiator and dormant polymer chain, but which does not form a direct carbon-metal bond with the polymer chain, is suitable for use in the present method. Thus, in one embodiment, the transition metal present in the catalyst is selected from the group that consists of Cu, Ni, Pd, Ru and Fe. In a preferred embodiment, the transition metal is copper (Cu), such as Cu(I) or Cu(II).

Suitable ligands for use in the present invention include ligands having one or more nitrogen, oxygen, phosphorous and/or sulphur atoms that can co-ordinate to the transition metal through a sigma-bond; ligands that contains two or more carbon atoms that can co-ordinate to the transition metal through a  $\pi$ -bond; and ligands that can co-ordinate to the transition metal through a  $\mu$ -bond or an  $\eta$ -bond. Accordingly, in one embodiment, the ligand comprises one or more N, O, P, S or C atoms that co-ordinate to the transition metal in the catalyst. In a spe-

cific embodiment, the ligand is N,N,N',N',N''-pentamethyldiethylenetriamine. As the skilled person in this field will realise the catalyst will be comprised of a transition metal complexed to a ligand, which complexing will take place more or less immediately after the ligand has been added to the suspension. For this reason, it is preferred to allow a relatively stable suspension to form before adding the ligand. As is well-known in this field, if the reaction is to be scaled-up to a suspension polymerisation reactor, then it is common to adjust the organic droplet size to roughly the size of the desired particles. Thus, in this case, it is preferred to adjust stirrer speed, allow droplet size to stabilise, readjust stirrer speed etc before adding the ligand. Accordingly, in the most advantageous embodiment, step (d) is performed a suitable period of time after step (c), e.g. after about 1 h. In this context, it is also noted that the ligand, which is water-soluble, should in some cases not be present in the aqueous phase before it is contacted with the organic phase, since it will then result in an immediate start of the polymerisation as soon as the two phases are contacted. In an alternative embodiment, the metal catalyst should not be present. As the skilled person in this field will realise, the factors that decides whether or not polymerisation will start immediately is the temperature and the nature of the monomers, hence the conditions are easily adapted from case to case to ensure that the polymerisation is not started until appropriate. This should be avoided, especially in cases where spherical particles are desired.

As mentioned above, the present method is performed under conditions that correspond to any conventional suspension polymerisation (for the basic principles of conventional suspension polymerisation, see e.g. J. R. Benson and D. J. Woo, J. Chromatographic Sci., 1984, 22, 386). Accordingly, the polymerisation can be performed at virtually any temperature below that where a substantial part of the aqueous phase will evaporate or the organic phase will boil. Thus, the temperature may e.g. be ambient temperature, and the reaction time can be

any period of time between about 5 minutes and up to several days, such as overnight.

The polymerisation is started according to step (d) by addition of a ligand that co-ordinates to the transition metal, whereby a catalyst is formed. The amount of ligand and transition metal used in the present method are those effective to conduct ATRP, see e.g. USP 5,763,548. More specifically, the molar proportion of ligand relative to the transition metal is generally that which is effective to polymerise the selected monomer(s), but can depend on the number of co-ordination sites on the transition metal which the ligand will occupy. The amount of ligand may be selected such that the ratio of (i) co-ordination sites on the transition metal to (ii) co-ordination sites, which the ligand will occupy, is from 0.1:1 to 100:1, such as 0.8:1 to 2:1.

In one embodiment, the removal according to step (e) is performed at basic or acidic conditions. Thus, a change of the pH in the environment can degrade the initiator molecule within the polymeric support. In another embodiment, the removal is performed by degradation of the initiator molecule by applying an external agent, such as heat and/or radiation and/or ultrasound. As the skilled person in this field will realise, the degrading conditions are dependent on the nature and chemical structure of the initiator molecule used. For example, a dendritic polyester macroinitiator can be removed by basic hydrolysis, as illustrated in the examples below. The results can be evaluated by any conventional method, such as Fourier transform infrared spectrometry (FTIR), titration and/or gravimetry. In a specific embodiment of the present method, the removal of the initiator molecule is quantitative. This can be advantageous as a control measure in cases where it is essential to confirm that no initiator molecule has been left in the polymeric support produced, e.g. in various bioprocesses, especially in the pharmaceutical field.

In an especially advantageous embodiment, the present method is used to produce cross-linked porous polymeric supports comprising one functionality or property within primary pores and the same or a different functionality or property within secondary pores. The method then comprises the method as described above and an additional step of selective surface modification of the supports so obtained after step (d) but before step (e). Such surface modification can for example be to introduce functional groups at chemical handles introduced as described above, which functional groups advantageously are ligands useful in chromatography, such as affinity groups, ion exchange groups or the like. Alternatively, the purpose of the surface modification can be to provide the surface of the primary pores with another property, such as hydrophobicity or hydrophilicity. Thus, in one embodiment, the surface available of the support obtained from step (d) is modified using acidic, neutral or basic conditions. The only requirement here is that the conditions used should not degrade the initiator molecule, unless the same modification is desired within both the primary and secondary pores.

The surface of the cavities left after removal of the initiator molecule according to step (e) will be provided with pendant groups resulting from breaking the bond of the ester or amide of the initiator molecule. In the case where the initiator molecule has been removed by hydrolysis, the pendant groups can for example be carboxylic groups. The pendant groups can after step (e) be converted, for example by reduction of carboxyl groups to yield hydroxyl or ether groups, by azido-decarboxylation and subsequent hydrolysis to yield amine groups. Alternatively, the pendant groups can be used to support ligands useful in chromatographic applications, in which case treatment with e.g.  $\text{SOCl}_2$  is followed by addition of ligand-hydroxyl groups or ligand-amine groups. In another embodiment, the surface of the cavities can be treated as discussed above in order to change its properties, e.g. to make it more hydrophobic or hydro-

philic. In a further embodiment, the surface is modified by polymerisation of linear or cross-linked polymer.

Accordingly, the external surface of the supports, the surface of the primary pores and the surface of the pores obtained after removal of the initiator molecule can be modified in any suitable way, depending on the desired use.

As mentioned above, in one embodiment of the present method, the secondary pore size is controlled by using an initiator molecule of a suitable molecular weight. Naturally, the larger initiator molecule used, the larger secondary pores will be obtained. In this context, it is essential to bear in mind that the polymeric supports must be sufficiently robust to not break during step (e).

A second aspect of the present invention is cross-linked porous polymeric support, which exhibits the above-described primary and secondary pore structure. Thus, in one embodiment, the polymeric support has been produced according to the method described above. In a specific embodiment, the polymeric support according to the invention is an essentially spherical particle having a diameter of about  $10\mu$ - $250\mu$  and wherein the absolute surface area is in a range of  $150$ - $500\text{ m}^2/\text{g}$ , such as  $300\text{ m}^2/\text{g}$ . The particles according to the invention are advantageously used as matrices in chromatography, where the large surface area thereof will increase their binding capacity as compared to prior art matrices. Also, the novel multimodal pore structure will contribute to improved mass transport properties.

However, for some isolation purposes columns packed with polymer particles are unsuitable because of the high level of back pressure created. Accordingly, in an alternative embodiment the support according to the invention is a monolith, such as a monolithic plug. The monolith has open passages therethrough, such as a honeycomb-shaped structure, and is desirable for applications

wherein a reasonably high rate of fluid flow and a low level of backpressure are required.

In an alternative embodiment, the support according to the invention is a membrane. Such a membrane will include a layer of polymeric support according to the invention fixed onto or attached to a base material according to well-known principles. Membranes are especially advantageous e.g. for large-scale operation, where high flow rates and high capacities are desired.

In an advantageous embodiment, the polymer particle according to the invention comprises one or more kind of chromatography ligands selected from the group affinity ligands, ion exchange ligand, etc bound to the surface of the primary pores and/or the secondary pores. In one embodiment, the surface of the primary and/or secondary pores has been rendered hydrophobic. In an alternative embodiment, the surface of the primary and/or secondary pores has been rendered hydrophilic.

The support according to the invention is accordingly useful for almost any isolation process wherein one or more target substances are separated from other components in a liquid. Thus, the support according to the invention can be used as a chromatographic adsorbent for isolation or separation of biomolecules, such as proteins, nucleic acids, such as plasmids, DNA or RNA, viruses etc, of other organic molecules, such as drug candidates, carbohydrates, or any inorganic compounds or molecules, depending on how they are modified. Similarly, the present method is also useful for purification of a liquid, from which removal of one or more of the above-exemplified target substances is desired. Thus, apart from the purification of a target compound or a liquid, the present invention is also useful for example in methods of combinatorial chemistry. The support according to the invention can also be used as a micro-

carrier for cell culture and as supports for solid-phase peptide or DNA synthesis.

A third aspect of the present invention is the use of a polymeric support according to the invention as a matrix in chromatography. The principles of different chromatographic separation methods, such as ion exchange chromatography, affinity chromatography, hydrophobic interaction chromatography etc are well known and have been thoroughly described in literature.

#### Detailed description of the drawings

Figure 1 (a) to (c) is a schematic drawing showing how an organic droplet phase (a) is polymerised by suspension polymerisation into a polymer particle (b) comprising a primary pore structure with areas of initiator molecule (dark areas), which is subsequently transformed into a polymer particle comprising a secondary pore structure (c) by removal of said initiator.

Figure 2 shows schematically some examples of possible surface modification of the secondary pore structure produced by removal of the initiator molecules according to the present invention. More specifically, a particle comprising an dendritic polyester (Boltorn®) and divinylbenzene is treated so that differing internal and external functionalities are obtained after hydrolysis.

Figure 3 shows schematically how the primary pore structure produced according to the present invention can be surface modified.

Figure 4 shows FTIR spectra of (a) beads A4; (b) beads B4; (c) beads E4; (d) beads F4; (e) beads G4; (f) beads H4 as described in detail in the examples below.

Figure 5 shows FTIR spectra of (a) beads A4; (b) beads C4; (c) degradation product of C4; (d) beads B4; (e) beads D4 as described in detail in the examples below.

Figure 6 is a A SEM photograph of a cross-section of beads A1 as described in detail in the examples below, see specifically example 2.

Figure 7 is a SEM photograph of a cross-section of beads B1 as described in detail in the examples below.

Figure 8 is a photograph of beads A1 obtained by optical light microscopy as described in detail in the examples below.

Figure 9 is a photograph of beads B1 obtained by optical light microscopy as described in detail in the examples below.

Figure 10 shows Table 1, naming polydivinylbenzene beads initiated by Boltorn®-BiB macroinitiators and mediated by CuCl/PMDETA, see example 2 below.

Figure 11 shows Table 2, illustrating the hydrolytic degradation of the polyester portion of poly(Boltorn®-BiB-divinylbenzene) beads, see example 3 below.


9  
10  
11  
12  
13  
14  
15  
16  
17  
18  
19  
20  
21  
22  
23  
24  
25  
26  
27  
28  
29  
30  
31  
32  
33  
34  
35  
36  
37  
38  
39  
40  
41  
42  
43  
44  
45  
46  
47  
48  
49  
50  
51  
52  
53  
54  
55  
56  
57  
58  
59  
60  
61  
62  
63  
64  
65  
66  
67  
68  
69  
70  
71  
72  
73  
74  
75  
76  
77  
78  
79  
80  
81  
82  
83  
84  
85  
86  
87  
88  
89  
90  
91  
92  
93  
94  
95  
96  
97  
98  
99  
100

### EXPERIMENTAL PART

Below, the present invention will be described in more detail by way of examples, which however are in no way intended to limit the scope of the present invention as defined by the appended claims. All references given below or elsewhere in the present specification are hereby included herein by reference.

#### Example 1: General procedure for the preparation of the polyester macroinitiators

##### *Example 1-1: Synthesis of Boltorn® 2-bromoisobutyryl ester, Boltorn® G2-BiB*




**Boltorn® G2-BiB**

Boltorn® G2 (3.50 g; 2 mmol), triethylamine (4.86 g; 48 mmol) and 4-(N,N-dimethylamino)pyridine (1.95 g; 16 mmol) were dissolved in dichloromethane (40 ml) and cooled to 0 °C in an ice bath. 2-Bromoisobutyryl bromide (8.83 g, 38.4 mmol) was dissolved in dichloromethane (10 ml) and added dropwise to the aforementioned solution. The reaction was allowed to proceed at room temperature overnight. The organic phase was extracted first with aq. NaHCO<sub>3</sub> (10%) and then with aq. NH<sub>4</sub>Cl (10%). The organic phase was dried over MgSO<sub>4</sub>, clarified with carbon black, and the solvent was removed under vac-

uum to give the product as pale-yellow oil. Yield 6.2 g (75%). FTIR (film/NaCl)  $\nu_{\text{max}}$  ( $\text{cm}^{-1}$ ) 2980, 1740, 1273, 1162, 766.  $^1\text{H}$  NMR ( $\text{CDCl}_3$ ):  $\delta_{\text{H}}$  (ppm) 1.20-1.40 (m, 36H,  $\text{CH}_3$ , Boltorn®), 1.91(s, 96H,  $\text{CH}_3$ , BiB), 3.30-3.80 (m, 20H,  $\text{CH}_2$ ), 4.30-4.40 (m, 56H,  $\text{CH}_2$ ).  $^{13}\text{C}$  NMR ( $\text{CDCl}_3$ ):  $\delta_{\text{C}}$  (ppm) 18, 31, 47, 55, 66, 171, 172.

*Example 1-2: Synthesis of Boltorn® 2-bromoisobutyryl ester, Boltorn® G3-BiB*




**Boltorn® G3-BiB**

Boltorn® G3 (10.0 g; 1.4 mmol) and triethylamine (13.4g; 67 mmol) were dissolved in tetrahydrofuran (30 ml) and cooled to 0 °C in an ice bath. 2-Bromoisobutyryl bromide (24.5 g, 53 mmol) was dissolved in tetrahydrofuran (24 ml) and added dropwise to the aforementioned solution. The reaction was allowed to proceed at room temperature for 3 hours. The solution was acidified with aq. HCl (37%) and filtered to remove triethylamine salts. The solvent was removed under vacuum and the resulting oil dried by coevaporation with toluene. The oil was dissolved in dichloromethane, the solution clarified with carbon black and filtered. The solvent was evaporated under vacuum. The crude

product was dissolved in a minimum amount of dichloromethane and precipitated into n-hexane. This operation was repeated until no impurities were detected by  $^1\text{H}$  NMR. The solvent was then removed under vacuum to give a pale-yellow solid. Yield 16.7g (72%). FTIR (film/NaCl)  $\nu_{\text{max}}$  ( $\text{cm}^{-1}$ ) 2980, 1740, 1273, 1162, 766.  $^1\text{H}$  NMR ( $\text{CDCl}_3$ ):  $\delta_{\text{H}}$  (ppm) 1.20-1.40 (m, 84H,  $\text{CH}_3$ , Boltorn®), 1.91(s, 192H,  $\text{CH}_3$ , BiB), 3.30-3.80 (m, 20H,  $\text{CH}_2$ ), 4.30-4.40 (m, 120H,  $\text{CH}_2$ ).  $^{13}\text{C}$  NMR ( $\text{CDCl}_3$ ):  $\delta_{\text{C}}$  (ppm) 18, 31, 47, 55, 66, 171, 172.

**Example 1-3: Synthesis of Boltorn® 2-bromoisobutyryl ester, Boltorn® G4-BiB**



**Boltorn® G4-BiB**

Boltorn® G4 (10.4 g; 0.68 mmol) and triethylamine (13.2 g; 66 mmol) were dissolved in dichloromethane (30ml) and cooled to 0 °C in an ice bath. 2-Bromoisobutyryl bromide (24.0 g, 52 mmol) was dissolved in dichloromethane (20 ml) and added dropwise to the aforementioned solution. The reaction was

allowed to proceed at room temperature for 3 hours. Dichloromethane was added to the reaction and the organic phase was extracted first with aq. HCl (2M) and then with aq. NaHCO<sub>3</sub>(10%). The organic phase was dried over MgSO<sub>4</sub>, clarified with carbon black, and the solvent was removed under vacuum. The resulting oil was dissolved in a minimum amount of dichloromethane and precipitated into n-hexane. This operation was repeated until no impurities were detected by <sup>1</sup>H NMR. The solvent was then removed under vacuum to give a pale-yellow solid. Yield 15.9 g (69%). FTIR (film/NaCl)  $\nu_{\max}$  (cm<sup>-1</sup>) 2980, 1740, 1273, 1162, 766. <sup>1</sup>H NMR (CDCl<sub>3</sub>):  $\delta_{\text{H}}$  (ppm) 1.20-1.40 (m, 180H, CH<sub>3</sub>, Boltorn®), 1.91(s, 384H, CH<sub>3</sub>, BiB), 3.30-3.80 (m, 20H, CH<sub>2</sub>), 4.30-4.40 (m, 248H, CH<sub>2</sub>). <sup>13</sup>C NMR (CDCl<sub>3</sub>):  $\delta_{\text{C}}$  (ppm) 18, 31, 47, 55, 66, 171, 172.

**Example 2: General procedure for the preparation of polydivinylbenzene beads initiated by Boltorn®-BiB macroinitiators and mediated by CuCl/PMDETA (Fig 10, Table 1)**

Divinylbenzene and Boltorn®-BiB macroinitiator were dissolved in toluene in a screw-top test tube. Ethyl-1-hexanol was added to the solution. The aqueous phase was made-up by combining an aqueous solution of Mowiol 40-88 with CuCl and aq. HCl. The aqueous phase was added to the vial and a suspension was created by shaking the vial. N,N,N',N',N''-pentamethylthriethylenediamine was added and the vial was shaken vigorously. The suspension was maintained for 24 hours at room temperature by rotating the vial at 60 rpm perpendicular to a parallel axis. The content of the vial was poured into boiling water. The beads were removed by filtration and washed with boiling water, ethanol and acetone. The beads were dried overnight under vacuum at 75 °C.

*Example 2-1: Preparation of polydivinylbenzene beads initiated by Boltorn® G3-BiB and mediated by CuCl/PMDETA (Beads A4)*

Divinylbenzene (4.90 ml; 4.48 g; 34.4 mmol) and Boltorn® G3-BiB (2.11 g; 0.25 mmol) were dissolved in toluene (2.10 ml) in a 50 ml screw-top glass test tube. 2-Ethyl-1-hexanol (4.90 ml) was added to the solution. The aqueous phase was made-up by combining an aqueous solution of Mowiol 40-88 (5%) (36 ml) with CuCl (0.24 g, 2.42 mmol) and aq. HCl (37%) (0.21 ml). The aqueous phase was added to the vial and a suspension was created by shaking the vial. N,N,N',N',N''-pentamethylthiethylenediamine (1.00 ml, 0.83g, 4.79 mmol) was added and the vial was shaken vigorously. The suspension was maintained for 24 hours at room temperature by rotating the vial at 60 rpm perpendicular to a parallel axis. The content of the vial was poured into boiling water (1000 ml). The beads were removed by filtration and washed with boiling water (8000 ml), ethanol (500 ml) and acetone (200 ml). The beads were dried overnight under vacuum at 75 °C. Yield 5.42 g (82%). FTIR (KBr)  $\nu_{\max}$  (cm<sup>-1</sup>) 3004 ((C-H)<sub>Ar</sub>), 2965 ((C-H)<sub>CH3</sub>), 2926 ((C-H)<sub>CH2</sub>), 1740 (C=O), 1628 (C=C)<sub>vinyl</sub>, 1596 (Ar-breathing), 1273-1162 (C-O-C) (Figure 4).

A SEM photograph of a cross-section of beads A1 is given as example in Figure 6.

A microphotograph of beads A1 obtained by optical light microscopy is given as example in Figure 8. Spherical beads being 10 - 60 µm i.d. were obtained.

**Example 3: General procedure for the hydrolytic degradation of the polyester portion of poly(Boltorn®-BiB-divinylbenzene) beads (Fig 11, Table 2)**

The poly(Boltorn®-BiB-divinylbenzene) beads were shaken in ethanolic NaOH (10%) at 50 °C for 24 hours. The obtained beads were removed by filtration and washed successively with ethanolic NaOH (10%), water, ethanol, ethanolic HCl (2 M), ethanol and acetone, and dried under vacuum at 75 °C.

*Example 3-1: Hydrolytic degradation of beads A4 (Beads B4)*

The poly(Boltorn®-BiB-divinylbenzene) beads A4 (0.1422 g) were shaken in ethanolic NaOH (10%) (20 ml) at 50 °C for 24 hours. The obtained beads were removed by filtration and washed with ethanolic NaOH (10%) (100 ml), water (1000 ml), ethanol (500 ml), ethanolic HCl (2 M) (500 ml), ethanol (500 ml) and acetone (200 ml) and dried under vacuum at 75 °C. Yield 0.1033 g. FTIR (KBr)  $\nu_{\max}$  (cm<sup>-1</sup>) 3030 and 3004 ((C-H)<sub>Ar</sub>), 2926 ((C-H)<sub>CH2</sub>), 1720-1700 (C=O), 1628 (C=C)<sub>vinyl</sub>, 1596 (Ar-breathing) (Figure 4).

A SEM photograph of a cross-section of beads B1 is given as example in Figure 7.

A microphotograph of beads B1 obtained by optical light microscopy is given as example in Figure 9. Spherical beads being 10 - 60 µm i.d. were obtained.

**Example 4: ATRP of MMA**

Beads, MMA, transition metal, ligand and solvent were combined and degassed with a N<sub>2</sub> stream for 15 minutes. The reaction vessel was sealed and heated to 60 °C for 48 hours. The beads were removed by filtration and washed with dichloromethane, ethanolic HCl (2M), ethanol and acetone. The beads were dried under vacuum at 75 °C for 24 hours.

*Example 4-1: ATRP of MMA using beads A4 (Beads C4)*

Beads A4 (0.1003 g), MMA (1.225 g, 12.2 mmol), CuCl (0.0118 g, 0.119 mmol), 2,2'-bipyridine (0.0380 g, 0.243 mmol) and anisole (1.308 ml) were combined and degassed with a N<sub>2</sub> stream for 15 minutes. The reaction vessel was sealed and heated to 60 °C for 48 hours. The beads were removed by filtration and washed with dichloromethane (200ml), ethanolic HCl (2M) (200

ml), ethanol (100 ml) and acetone (200 ml). The beads were dried under vacuum at 75 °C for 24 hours. Yield 0.2300g; 12.9 mmol MMA units per gram starting material. A FTIR spectrum is shown in Figure 5.

*Example 4-2: ATRP of MMA using beads B4 (Beads D4)*

Beads B4 (0.0408 g), MMA (0.668 g, 6.85 mmol), CuCl (0.0076 g, 0.077 mmol), 2,2'-bipyridine (0.0207 g, 0.132 mmol) and anisole (0.735 ml) were combined and degassed with a N<sub>2</sub> stream for 15 minutes. The reaction vessel was sealed and heated to 60 °C for 48 hours. The beads were removed by filtration and washed with dichloromethane (200ml), ethanolic HCl (2M) (200 ml), ethanol (100 ml) and acetone (200 ml). The beads were dried under vacuum at 75 °C for 24 hours. Yield 0.0523g; 2.82 mmol MMA units per gram starting material. A FTIR spectrum is shown in Figure 5.

**Example 5: Sulphonation using beads A4 (Beads E4)**

Beads A4 (5.00 g) were slurred in chloroform (25 ml). Chlorosulphonic acid (23 ml, 40.7 g, 350 mmol) was added in several portions to the reaction mixture. The reaction was shaken at room temperature overnight. The beads were filtered and washed with dichloromethane (500 ml) and acetone (200 ml). The beads were shaken overnight in aq. NaHCO<sub>3</sub> (10%) (50 ml). The beads were removed by filtration and washed with aq. NaHCO<sub>3</sub> (10%) (200 ml), aq. HCl (2M) (200ml), ethanol (200ml), acetone (200ml) and ether (100ml) and dried under vacuum at 75 °C overnight to give orange beads. Yield 5.99 g. FTIR (KBr)  $\nu_{\max}$  (cm<sup>-1</sup>) 3463 (S-OH), 3030 ((C-H)<sub>Ar</sub>), 2965 ((C-H)<sub>CH3</sub>), 2926 ((C-H)<sub>CH2</sub>), 1740 (C=O), 1596 (Ar-breathing), 1211 and 1177 (O=S=O) (Figure 4).

**Example 6: Chlorination of beads E4 (Beads F4)**

Thionyl chloride (20 ml, 274 mmol) was added slowly to the dried beads (3.97 g) under a N<sub>2</sub> stream and the flask was sealed and shaken at 60 °C for 48 hours. The beads were filtered and washed with chloroform (300 ml) and dried under vacuum at 75 °C over one day to give brown/purple beads. Yield 3.94 g. FTIR (KBr)  $\nu_{\max}$  (cm<sup>-1</sup>) 3030 ((C-H)<sub>Ar</sub>), 2965 ((C-H)<sub>CH3</sub>), 2926 ((C-H)<sub>CH2</sub>), 1740 (C=O), 1596 (Ar-breathing), 1371 and 1172 (O=S=O) (Figure 4).

**Example 7: Synthesis of 2-(aminomethyl)pyridine sulphonamide derivative from beads F4 (Beads G4)**

Beads F4 (0.4876 g) were slurried in dichloromethane (5 ml) and cooled to 0 °C. 2-(aminomethyl)pyridine (1.88 g; 17.4 mmol) was dissolved in dichloromethane (5 ml) and cooled to 0 °C. The above solution was slowly added to the beads slurry under constant shaking. The reaction was heated to 50 °C and shaken for 24 hours. The beads were removed by filtration and washed with ethanol (99.5%) (100 ml), water (100 ml), ethanol (99.5%) (100 ml), acetone (100 ml) and dichloromethane (100ml). Yield: 0.4956 g. FTIR (KBr)  $\nu_{\max}$  (cm<sup>-1</sup>) 3280 (N-H), 3030 and 3010 ((C-H)<sub>Ar</sub>), 2965 ((C-H)<sub>CH3</sub>), 2926 ((C-H)<sub>CH2</sub>), 1740 (C=O), 1596 (Ar-breathing), 1327 and 1172 (O=S=O) (Figure 4).

**Example 8: Hydrolytic degradation of beads G4 (Beads H4)**

Beads G4 (0.1565 g) were shaken in ethanolic NaOH (10%) (20 ml) at 50 °C for 24 hours. The obtained beads were removed by filtration and washed with ethanolic NaOH (10%) (100 ml), water (1 L), ethanol (500 ml), ethanolic HCl (2 M) (500 ml), ethanol (500 ml) and acetone (200 ml) and dried under vacuum at 75 °C. Yield 0.1275 g. FTIR (KBr)  $\nu_{\max}$  (cm<sup>-1</sup>) 3280 (N-H), 3030 and 3010 ((C-H)<sub>Ar</sub>), 2965 ((C-H)<sub>CH3</sub>), 2926 ((C-H)<sub>CH2</sub>), 2800-2400 (O-H)<sub>acid H-bonded</sub>, 1700 (C=O), 1596 (Ar-breathing), 1327 and 1172 (O=S=O) (Figure 4).

CLAIMS

1. A method of producing a cross-linked polymeric support having a multimodal pore structure, which method comprises the steps of
  - (a) providing a degradable initiator molecule;
  - (b) providing an organic phase, which comprises said initiator molecule, one or more radically polymerisable monomers and a porogen in a solvent, and an aqueous phase, which comprises a transition metal catalyst;
  - (c) forming a suspension of the organic phase and the aqueous phase;
  - (d) starting a suspension polymerisation of the organic phase in the aqueous phase by adding a ligand, which co-ordinates to the transition metal in the aqueous phase via at least one atom, to produce a cross-linked polymeric support having a primary pore structure and comprising initiator molecule; and
  - (e) subjecting the support obtained from step (d) to degrading conditions to at least partially remove the initiator molecule from within the support to produce a cross-linked polymeric support having a secondary pore structure in addition to the primary pore structure.
2. A method according to claim 1, wherein the initiator molecule is a macro-initiator.
3. A method according to claim 1 or 2, wherein step (a) comprises to react a compound that comprises at least one hydroxy group, primary amine group or secondary amine group with an alfa-haloacyl halide.
4. A method according to claim 3, wherein a hydroxy-functional dendritic polyester is reacted with the alfa-haloacyl halide.
5. A method according to claim 3, wherein an amino-functional dendritic polyamide is reacted with the alfa-haloacyl halide.
6. A method according to any one of the preceding claims, wherein in step (d), the organic phase comprises up to about 50%, such as about 30%, of the initiator molecule, calculated as weight/weight monomer.

7. A method according to any one of the preceding claims, wherein the monomers are synthetic mono and/or multifunctional monomers, such as styrene and/or divinyl benzene.
8. A method according to any one of the preceding claims, wherein the transition metal is selected from the group that consists of Cu, Ni, Pd, Ru and Fe.
9. A method according to any one of the preceding claims, wherein the ligand comprises one or more N, O, P, S or C atoms that co-ordinated to the transition metal to form a catalyst system.
10. A method according to any one of the preceding claims, wherein the removal according to step (e) is performed under basic or acidic conditions.
11. A method according to any one of the preceding claims, wherein the removal according to step (e) is performed by applying an external agent, such as heat and/or radiation and/or ultrasound.
12. A method of producing a cross-linked polymeric support comprising one functionality within a primary pore structure and one functionality within a secondary pore structure, which comprises a method according to any one of the preceding claims and an additional step of selective surface modification of the supports so obtained after step (d) but before step (e).
13. A method according to claim 12, wherein the surface of the support obtained from step (d) is modified using conditions that have no essential impact on the initiator molecule present in the support.
14. A method according to any one of the preceding claims, wherein the secondary pore size is controlled by the molecular weight of the initiator molecule.
15. A cross-linked porous polymeric support, which has been produced according to any one of claims 1-14.
16. A polymeric support according to claim 15, which is comprised of one or more essentially spherical particles having a diameter of about 10 $\mu$ m and 250 $\mu$ m, wherein the specific surface area is in a range of 150-300 m<sup>2</sup>/g.
17. A polymeric support according to claim 15, which is a monolith.

18. A polymeric support according to any one of claims 15-17, which comprises functional groups, such as chromatography ligands, coupled to the surface of the primary pores and/or the secondary pores.
19. Use of a polymeric support according to any one of claims 15-18 as a matrix in chromatography.

### ABSTRACT


The present invention relates to a method of producing a cross-linked polymeric support having a multimodal pore structure, which method comprises the steps of providing a degradable initiator molecule; providing an organic phase comprising said initiator molecule, one or more radically polymerisable monomers and a porogen in a solvent; providing an aqueous phase comprising a transition metal catalyst; starting a suspension polymerisation of the organic phase in the aqueous phase by adding a ligand, which co-ordinates to the transition metal in the aqueous phase via at least one atom, to produce a cross-linked polymeric support having a primary pore structure and comprising initiator molecule; and subjecting the support obtained to degrading conditions to at least partially remove the initiator molecule from within the support to produce a cross-linked polymeric support having a secondary pore structure in addition to the primary pore structure.

The invention also relates to a support produced according to the method above, e.g. in the form of particles, a monolith or a membrane.

9  
1  
2  
3  
4  
5  
6  
7  
8  
9  
10  
11  
12  
13  
14  
15  
16  
17  
18  
19  
20  
21  
22  
23  
24  
25  
26  
27  
28  
29  
30  
31  
32  
33  
34  
35  
36  
37  
38  
39  
40  
41  
42  
43  
44  
45  
46  
47  
48  
49  
50  
51  
52  
53  
54  
55  
56  
57  
58  
59  
60  
61  
62  
63  
64  
65  
66  
67  
68  
69  
70  
71  
72  
73  
74  
75  
76  
77  
78  
79  
80  
81  
82  
83  
84  
85  
86  
87  
88  
89  
90  
91  
92  
93  
94  
95  
96  
97  
98  
99  
100  
101  
102  
103  
104  
105  
106  
107  
108  
109  
110  
111  
112  
113  
114  
115  
116  
117  
118  
119  
120  
121  
122  
123  
124  
125  
126  
127  
128  
129  
130  
131  
132  
133  
134  
135  
136  
137  
138  
139  
140  
141  
142  
143  
144  
145  
146  
147  
148  
149  
150  
151  
152  
153  
154  
155  
156  
157  
158  
159  
160  
161  
162  
163  
164  
165  
166  
167  
168  
169  
170  
171  
172  
173  
174  
175  
176  
177  
178  
179  
180  
181  
182  
183  
184  
185  
186  
187  
188  
189  
190  
191  
192  
193  
194  
195  
196  
197  
198  
199  
200  
201  
202  
203  
204  
205  
206  
207  
208  
209  
210  
211  
212  
213  
214  
215  
216  
217  
218  
219  
220  
221  
222  
223  
224  
225  
226  
227  
228  
229  
230  
231  
232  
233  
234  
235  
236  
237  
238  
239  
240  
241  
242  
243  
244  
245  
246  
247  
248  
249  
250  
251  
252  
253  
254  
255  
256  
257  
258  
259  
260  
261  
262  
263  
264  
265  
266  
267  
268  
269  
270  
271  
272  
273  
274  
275  
276  
277  
278  
279  
280  
281  
282  
283  
284  
285  
286  
287  
288  
289  
290  
291  
292  
293  
294  
295  
296  
297  
298  
299  
300  
301  
302  
303  
304  
305  
306  
307  
308  
309  
310  
311  
312  
313  
314  
315  
316  
317  
318  
319  
320  
321  
322  
323  
324  
325  
326  
327  
328  
329  
330  
331  
332  
333  
334  
335  
336  
337  
338  
339  
340  
341  
342  
343  
344  
345  
346  
347  
348  
349  
350  
351  
352  
353  
354  
355  
356  
357  
358  
359  
360  
361  
362  
363  
364  
365  
366  
367  
368  
369  
370  
371  
372  
373  
374  
375  
376  
377  
378  
379  
380  
381  
382  
383  
384  
385  
386  
387  
388  
389  
390  
391  
392  
393  
394  
395  
396  
397  
398  
399  
400  
401  
402  
403  
404  
405  
406  
407  
408  
409  
410  
411  
412  
413  
414  
415  
416  
417  
418  
419  
420  
421  
422  
423  
424  
425  
426  
427  
428  
429  
430  
431  
432  
433  
434  
435  
436  
437  
438  
439  
440  
441  
442  
443  
444  
445  
446  
447  
448  
449  
450  
451  
452  
453  
454  
455  
456  
457  
458  
459  
460  
461  
462  
463  
464  
465  
466  
467  
468  
469  
470  
471  
472  
473  
474  
475  
476  
477  
478  
479  
480  
481  
482  
483  
484  
485  
486  
487  
488  
489  
490  
491  
492  
493  
494  
495  
496  
497  
498  
499  
500  
501  
502  
503  
504  
505  
506  
507  
508  
509  
510  
511  
512  
513  
514  
515  
516  
517  
518  
519  
520  
521  
522  
523  
524  
525  
526  
527  
528  
529  
530  
531  
532  
533  
534  
535  
536  
537  
538  
539  
540  
541  
542  
543  
544  
545  
546  
547  
548  
549  
550  
551  
552  
553  
554  
555  
556  
557  
558  
559  
560  
561  
562  
563  
564  
565  
566  
567  
568  
569  
570  
571  
572  
573  
574  
575  
576  
577  
578  
579  
580  
581  
582  
583  
584  
585  
586  
587  
588  
589  
590  
591  
592  
593  
594  
595  
596  
597  
598  
599  
600  
601  
602  
603  
604  
605  
606  
607  
608  
609  
610  
611  
612  
613  
614  
615  
616  
617  
618  
619  
620  
621  
622  
623  
624  
625  
626  
627  
628  
629  
630  
631  
632  
633  
634  
635  
636  
637  
638  
639  
640  
641  
642  
643  
644  
645  
646  
647  
648  
649  
650  
651  
652  
653  
654  
655  
656  
657  
658  
659  
660  
661  
662  
663  
664  
665  
666  
667  
668  
669  
670  
671  
672  
673  
674  
675  
676  
677  
678  
679  
680  
681  
682  
683  
684  
685  
686  
687  
688  
689  
690  
691  
692  
693  
694  
695  
696  
697  
698  
699  
700  
701  
702  
703  
704  
705  
706  
707  
708  
709  
710  
711  
712  
713  
714  
715  
716  
717  
718  
719  
720  
721  
722  
723  
724  
725  
726  
727  
728  
729  
730  
731  
732  
733  
734  
735  
736  
737  
738  
739  
740  
741  
742  
743  
744  
745  
746  
747  
748  
749  
750  
751  
752  
753  
754  
755  
756  
757  
758  
759  
760  
761  
762  
763  
764  
765  
766  
767  
768  
769  
770  
771  
772  
773  
774  
775  
776  
777  
778  
779  
780  
781  
782  
783  
784  
785  
786  
787  
788  
789  
790  
791  
792  
793  
794  
795  
796  
797  
798  
799  
800  
801  
802  
803  
804  
805  
806  
807  
808  
809  
810  
811  
812  
813  
814  
815  
816  
817  
818  
819  
820  
821  
822  
823  
824  
825  
826  
827  
828  
829  
830  
831  
832  
833  
834  
835  
836  
837  
838  
839  
840  
841  
842  
843  
844  
845  
846  
847  
848  
849  
850  
851  
852  
853  
854  
855  
856  
857  
858  
859  
860  
861  
862  
863  
864  
865  
866  
867  
868  
869  
870  
871  
872  
873  
874  
875  
876  
877  
878  
879  
880  
881  
882  
883  
884  
885  
886  
887  
888  
889  
890  
891  
892  
893  
894  
895  
896  
897  
898  
899  
900  
901  
902  
903  
904  
905  
906  
907  
908  
909  
910  
911  
912  
913  
914  
915  
916  
917  
918  
919  
920  
921  
922  
923  
924  
925  
926  
927  
928  
929  
930  
931  
932  
933  
934  
935  
936  
937  
938  
939  
940  
941  
942  
943  
944  
945  
946  
947  
948  
949  
950  
951  
952  
953  
954  
955  
956  
957  
958  
959  
960  
961  
962  
963  
964  
965  
966  
967  
968  
969  
970  
971  
972  
973  
974  
975  
976  
977  
978  
979  
980  
981  
982  
983  
984  
985  
986  
987  
988  
989  
990  
991  
992  
993  
994  
995  
996  
997  
998  
999  
1000  
1001  
1002  
1003  
1004  
1005  
1006  
1007  
1008  
1009  
1010  
1011  
1012  
1013  
1014  
1015  
1016  
1017  
1018  
1019  
1020  
1021  
1022  
1023  
1024  
1025  
1026  
1027  
1028  
1029  
1030  
1031  
1032  
1033  
1034  
1035  
1036  
1037  
1038  
1039  
1040  
1041  
1042  
1043  
1044  
1045  
1046  
1047  
1048  
1049  
1050  
1051  
1052  
1053  
1054  
1055  
1056  
1057  
1058  
1059  
1060  
1061  
1062  
1063  
1064  
1065  
1066  
1067  
1068  
1069  
1070  
1071  
1072  
1073  
1074  
1075  
1076  
1077  
1078  
1079  
1080  
1081  
1082  
1083  
1084  
1085  
1086  
1087  
1088  
1089  
1090  
1091  
1092  
1093  
1094  
1095  
1096  
1097  
1098  
1099  
1100  
1101  
1102  
1103  
1104  
1105  
1106  
1107  
1108  
1109  
1110  
1111  
1112  
1113  
1114  
1115  
1116  
1117  
1118  
1119  
1120  
1121  
1122  
1123  
1124  
1125  
1126  
1127  
1128  
1129  
1130  
1131  
1132  
1133  
1134  
1135  
1136  
1137  
1138  
1139  
1140  
1141  
1142  
1143  
1144  
1145  
1146  
1147  
1148  
1149  
1150  
1151  
1152  
1153  
1154  
1155  
1156  
1157  
1158  
1159  
1160  
1161  
1162  
1163  
1164  
1165  
1166  
1167  
1168  
1169  
1170  
1171  
1172  
1173  
1174  
1175  
1176  
1177  
1178  
1179  
1180  
1181  
1182  
1183  
1184  
1185  
1186  
1187  
1188  
1189  
1190  
1191  
1192  
1193  
1194  
1195  
1196  
1197  
1198  
1199  
1200  
1201  
1202  
1203  
1204  
1205  
1206  
1207  
1208  
1209  
1210  
1211  
1212  
1213  
1214  
1215  
1216  
1217  
1218  
1219  
1220  
1221  
1222  
1223  
1224  
1225  
1226  
1227  
1228  
1229  
1230  
1231  
1232  
1233  
1234  
1235  
1236  
1237  
1238  
1239  
1240  
1241  
1242  
1243  
1244  
1245  
1246  
1247  
1248  
1249  
1250  
1251  
1252  
1253  
1254  
1255  
1256  
1257  
1258  
1259  
1260  
1261  
1262  
1263  
1264  
1265  
1266  
1267  
1268  
1269  
1270  
1271  
1272  
1273  
1274  
1275  
1276  
1277  
1278  
1279  
1280  
1281  
1282  
1283  
1284  
1285  
1286  
1287  
1288  
1289  
1290  
1291  
1292  
1293  
1294  
1295  
1296  
1297  
1298  
1299  
1300  
1301  
1302  
1303  
1304  
1305  
1306  
1307  
1308  
1309  
1310  
1311  
1312  
1313  
1314  
1315  
1316  
1317  
1318  
1319  
1320  
1321  
1322  
1323  
1324  
1325  
1326  
1327  
1328  
1329  
1330  
1331  
1332  
1333  
1334  
1335  
1336  
1337  
1338  
1339  
1340  
1341  
1342  
1343  
1344  
1345  
1346  
1347  
1348  
1349  
1350  
1351  
1352  
1353  
1354  
1355  
1356  
1357  
1358  
1359  
1360  
1361  
1362  
1363  
1364  
1365  
1366  
1367  
1368  
1369  
1370  
1371  
1372  
1373  
1374  
1375  
1376  
1377  
1378  
1379  
1380  
1381  
1382  
1383  
1384  
1385  
1386  
1387  
1388  
1389  
1390  
1391  
1392  
1393  
1394  
1395  
1396  
1397  
1398  
1399  
1400  
1401  
1402  
1403  
1404  
1405  
1406  
1407  
1408  
1409  
1410  
1411  
1412  
1413  
1414  
1415  
1416  
1417  
1418  
1419  
1420  
1421  
1422  
1423  
1424  
1425  
1426  
1427  
1428  
1429  
1430  
1431  
1432  
1433  
1434  
1435  
1436  
1437  
1438  
1439  
1440  
1441  
1442  
1443  
1444  
1445  
1446  
1447  
1448  
1449  
1450  
1451  
1452  
1453  
1454  
1455  
1456  
1457  
1458  
1459  
1460  
1461  
1462  
1463  
1464  
1465  
1466  
1467  
1468  
1469  
1470  
1471  
1472  
1473  
1474  
1475  
1476  
1477  
1478  
1479  
1480  
1481  
1482  
1483  
1484  
1485  
1486  
1487  
1488  
1489  
1490  
1491  
1492  
1493  
1494  
1495  
1496  
1497  
1498  
1499  
1500  
1501  
1502  
1503  
1504  
1505  
1506  
1507  
1508  
1509  
1510  
1511  
1512  
1513  
1514  
1515  
1516  
1517  
1518  
1519  
1520  
1521  
1522  
1523  
1524  
1525  
1526  
1527  
1528  
1529  
1530  
1531  
1532  
1533  
1534  
1535  
1536  
1537  
1538  
1539  
1540  
1541  
1542  
1543  
1544  
1545  
1546  
1547  
1548  
1549  
1550  
1551  
1552  
1553  
1554  
1555  
1556  
1557  
1558  
1559  
1560  
1561  
1562  
1563  
1564  
1565  
1566  
1567  
1568  
1569  
1570  
1571  
1572  
1573  
1574  
1575  
1576  
1577  
1578  
1579  
1580  
1581  
1582  
1583  
1584  
1585  
1586  
1587  
1588  
1589  
1590  
1591  
1592  
1593  
1594  
1595  
1596  
1597  
1598  
1599  
1600  
1601  
1602  
1603  
1604  
1605  
1606  
1607  
1608  
1609  
1610  
1611  
1612  
1613  
1614  
1615  
1616  
1617  
1618  
1619  
1620  
1621  
1622  
1623  
1624  
1625  
1626  
1627  
1628  
1629  
1630  
1631  
1632  
1633  
1634  
1635  
1636  
1637  
1638  
1639  
1640  
1641  
1642  
1643  
1644  
1645  
1646  
1647  
1648  
1649  
1650  
1651  
1652  
1653  
1654  
1655  
1656  
1657  
1658  
1659  
1660  
1661  
1662  
1663  
1664  
1665  
1666  
1667  
1668  
1669  
1670  
1671  
1672  
1673  
1674  
1675  
1676  
1677  
1678  
1679  
1680  
1681  
1682  
1683  
1684  
1685  
1686  
1687  
1688  
1689  
1690  
1691  
1692  
1693  
1694  
1695  
1696  
1697  
1698  
1699  
1700  
1701  
1702  
1703  
1704  
1705  
1706  
1707  
1708  
1709  
1710  
1711  
1712  
1713  
1714  
1715  
1716  
1717  
1718  
1719  
1720  
1721  
1722  
1723  
1724  
1725  
1726  
1727  
1728  
1729  
1730  
1731  
1732  
1733  
1734  
1735  
1736  
1737  
1738  
1739  
1740  
1741  
1742  
1743  
1744  
1745  
1746  
1747  
1748  
1749  
1750  
1751  
1752  
1753  
1754  
1755  
1756  
1757  
1758  
1759  
1760  
1761  
1762  
1763  
1764  
1765  
1766  
1767  
1768  
1769  
1770  
1771  
1772  
1773  
1774  
1775  
1776  
1777  
1778  
1779  
1780  
1781  
1782  
1783  
1784  
1785  
1786  
1787  
1788  
1789  
1790  
1791  
1792  
1793  
1794  
1795  
1796  
1797  
1798  
1799  
1800  
1801  
1802  
1803  
1804  
1805  
1806  
1807  
1808  
1809  
1810  
1811  
1812  
1813  
1814  
1815  
1816  
1817  
1818  
1819  
1820  
1821  
1822  
1823  
1824  
1825  
1826  
1827  
1828  
1829  
1830  
1831  
1832  
1833  
1834  
1835  
1836  
1837  
1838  
1839  
1840  
1841  
1842  
1843  
1844  
1845  
1846  
1847  
1848  
1849  
1850  
1851  
1852  
1853  
1854  
1855  
1856  
1857  
1858  
1859  
1860  
1861  
1862  
1863  
1864  
1865  
1866  
1867  
1868  
1869  
1870  
1871  
1872  
1873  
1874  
1875  
1876  
1877  
1878  
1879  
1880  
1881  
1882  
1883  
1884  
1885  
1886  
1887  
1888  
1889  
1890  
1891  
1892  
1893  
1894  
1895  
1896  
1897  
1898  
1899  
1900  
1901  
1902  
1903  
1904  
1905  
1906  
1907  
1908  
1909  
1910  
1911  
1912  
1913  
1914  
1915  
1916  
1917  
1918  
1919  
1920  
1921  
1922  
1923  
1924  
1925  
1926  
1927  
1928  
1929  
1930  
1931  
1932  
1933  
1934  
1935  
1936  
1937  
1938  
1939  
1940  
1941  
1942  
1943  
1944  
1945  
1946  
1947  
1948  
1949  
1950  
1951  
1952  
1953  
1954  
1955  
1956  
1957  
1958  
1959  
1960  
1961  
1962  
1963  
1964  
1965  
1966  
1967  
1968  
1969  
1970  
1971  
1972  
1973  
1974  
1975  
1976  
1977  
1978  
1979  
1980  
1981  
1982  
1983  
1984  
1985  
1986  
1987  
1988  
1989  
1990  
1991  
1992  
1993  
1994  
1995  
1996  
1997  
1998  
1999  
2000  
2001  
2002  
2003  
2004  
2005  
2006  
2007  
2008  
2009  
2010  
2011  
2012  
2013  
2014  
2015  
2016  
2017  
2018  
2019  
2020  
2021  
2022  
2023  
2024  
2025  
2026  
2027  
2028  
2029  
2030  
2031  
2032  
2033  
2034  
2035  
2036  
2037  
2038  
2039  
2040  
2041  
2042  
2043  
2044  
2045  
2046  
2047  
2048  
2049  
2050  
2051  
2052  
2053  
2054  
2055  
2056  
2057  
2058  
2059  
2060  
2061  
2062  
2063  
2064  
2065  
2066  
2067  
2068  
2069  
2070  
2071  
2072  
2073  
2074  
2075  
2076  
2077  
2078  
2079  
2080  
2081  
2082  
2083  
2084  
2085  
2086  
2087  
2088  
2089  
2090  
2091  
2092  
2093  
2094  
2095  
2096  
2097  
2098  
2099  
2100  
2101  
2102  
2103  
2104  
2105  
2106  
2107  
2108  
2109  
2110  
2111  
2112  
2113  
2114  
2115  
2116  
2117  
2118  
2119  
2120  
2121  
2122  
2123  
2124  
2125  
2126  
2127  
2128  
2129  
2130  
2131  
2132  
2133  
2134  
2135  
2136  
2137  
2138  
2139  
2140  
2141  
2142  
2143  
2144  
2145  
2146  
2147  
2148  
2149  
2150  
2151  
2152  
2153  
2154  
2155  
2156  
2157  
2158  
2159  
2160  
2161  
2162  
2163  
2164  
2165  
2166  
2167  
2168  
2169  
2170  
2171  
2172  
2173  
2174  
2175  
2176  
2177  
2178  
2179  
2180  
2181  
2



3) degradation  
4) wash residues



1) polymerisation  
2) wash out porogen





Figure 1.

0000016-2

[illegible]

NAV 02-05-07

Figure 3.



000015-3

PRV 020627




Figure 4.





Figure 5.

0000016-2




PPV 02:08:27

**Figure 7.**



0000014-3

Figure 8.



**Figure 9.**




Figure 10.

Table 1: Polydivinylbenzene beads initiated by Boltorn®-BiB macroinitiators and mediated by CuCl/PMDETA

Beads	Boltorn®-BiB		DVB (g)		Porogen		Yield (%)	Before hydrolysis	
	Generation	Mass (g)			Toluene (ml)	2-Ethyl-1-hexanol (ml)		Surface area (m <sup>2</sup> g <sup>-1</sup> )	Adsorption pore volume (ml g <sup>-1</sup> )
A1 <sup>a</sup>	2 <sup>nd</sup>	0.33	0.60	0.33	0.66	0.66	86	134	0.3742
A2 <sup>b</sup>	2 <sup>nd</sup>	0.15	0.27	0.22	0.45	0.45	82	65	0.1872
A3 <sup>b</sup>	2 <sup>nd</sup>	0.30	0.27	0.30	0.30	0.30	79	1	0.0067
A4 <sup>c</sup>	3 <sup>rd</sup>	2.11	4.48	2.10	4.90	4.90	82	117	0.3354
A5 <sup>c</sup>	3 <sup>rd</sup>	1.53	3.26	1.99	4.64	4.64	81	73	0.1833
A6 <sup>d</sup>	4 <sup>th</sup>	0.17	0.37	0.17	0.40	0.40	94	64	0.1547
A7 <sup>e</sup>	4 <sup>th</sup>	0.75	1.60	0.97	2.27	2.27	91	140	0.3210

<sup>a</sup>Sealed test tube reactor, 12 ml; 9 ml Mowiol (5%), 0.03 ml HCl (37%), 0.18 ml PMDETA, 0.044 g CuCl

<sup>b</sup>Sealed test tube reactor, 5 ml; 3 ml Mowiol (5%), 0.03 ml HCl (37%), 0.092 ml PMDETA, 0.022 g CuCl

<sup>c</sup>Sealed test tube reactor, 50 ml; 36 ml Mowiol (5%), 0.21 ml HCl (37%), 1 ml PMDETA, 0.22 g CuCl

<sup>d</sup>Sealed test tube reactor, 5 ml; 3 ml Mowiol (2%), 0.03 ml HCl (37%), 0.092 ml PMDETA, 0.022 g CuCl

<sup>e</sup>Sealed test tube reactor, 25 ml; 16 ml Mowiol (2%), 0.13 ml HCl (37%), 0.46 ml PMDETA, 0.11 g CuCl

Figure 11.

Table 2: Hydrolytic degradation of the polyester portion of poly(Boltorn®-BiB-divinylbenzene) beads

Beads	Boltorn®-BiB		Wt% DVB	Amount of initiation sites in feed (mmol g <sup>-1</sup> )	After hydrolysis				
	Generation	Wt%			% Retention of resin <sup>a</sup>	Carboxylic acid group capacity (mmol g <sup>-1</sup> ) <sup>b</sup>	% Conversion of initiation sites <sup>c</sup>	Surface area (m <sup>2</sup> g <sup>-1</sup> )	Adsorption pore volume (ml g <sup>-1</sup> )
B1	2 <sup>nd</sup>	35.4	64.6	1.37	66.7	0.56	27	281	0.4955
B2	2 <sup>nd</sup>	35.4	64.6	1.37	69.8	1.35	69	142	N/A
B3	2 <sup>nd</sup>	52.2	47.8	2.02	57.4	0.80	23	90	0.0731
B4	3 <sup>rd</sup>	32.0	68.0	1.22	72.6	0.86	51	199	0.4943
B5	3 <sup>rd</sup>	31.9	68.1	1.22	80.6	0.84	56	245	0.2997
B6	4 <sup>th</sup>	31.9	68.1	1.21	71.4	0.78	46	171	0.3448
B7	4 <sup>th</sup>	31.9	68.1	1.21	79.1	0.56	36	291	0.4249

<sup>a</sup>Determined by gravimetry

<sup>b</sup>Determined by titration

<sup>c</sup>Calculated as, (carboxylic acid group capacity/ retention of resin)/ amount of initiation sites in feed

**This Page is Inserted by IFW Indexing and Scanning  
Operations and is not part of the Official Record**

**BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☒ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** \_\_\_\_\_

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.**